

# ●アプリケーション

合金種類	色あい	平打ち	型押し・深絞り	打ち抜き・プレス	エナメル加工	鑄造	チェーン	飾りピン・束	型押し	管・蝶番	溶接	グラニニール	パベセッティング	結婚指輪
<b>カラーゴールド</b>														
8K 333/75	山吹色	●	●	●			●		●	●			●	●
8K 333/90*	ローズ	●					●							
8K 333/120	淡黄色	●	●	●		●			●	●			●	●
9K 376/60	山吹色	●					●			●				
9K 375/120*	黄	●	●	●		●	●						●	
14K 585/40	赤	●	●	●	●		●							
14K 585/45*	黄	●	●	●		●	●		●				●	●
14K 585/100*	ローズ	●				●		●						
14K 585/200*	山吹色	●						●						●
14K 585/260	黄色	●				●	●							●
14K 585/300	淡黄色	●	●	●	●	●	●		●	●		●	●	●
14K 585/340	緑黄色		●	●	●	●	●		●				●	
18K 750/40	赤	●				●		●			●	●		
18K 750/90	ローズ	●				●		●						
18K 750/125	山吹色	●	●	●	●	●	●		●				●	●
18K 750/130	山吹色	●	●	●	●	●	●		●	●			●	●
18K 750/150	淡黄色	●	●	●	●	●	●		●	●	●	●	●	●
21K 900/-*	ローズ				●			●						
21K 900/50	山吹色	●	●		●	●		●	●	●	●	●	●	●
22K 917/53*	山吹色	●	●		●			●		●			●	
23K 990/-	山吹色	●						●						
<b>ホワイトゴールド</b>														
8K 333/585*	白 Ag	●	●	●		●			●					●
9K 375/560	白 Ag	●	●	●					●					
14K 585 S2	白 14% Pd	●												
14K 587 H2*	白 7% Ni					●								
14K 590 H1*	白 10% Ni	●						●						
14K 588 E*	白 Mn												●	●
14K 585 S*	白 10% Pd	●	●	●					●				●	
14K 585 M	白 19% Pd	●						●		●				●
18K 752 H2	白 6% Ni					●								
18K 760 H1	白 10% Ni	●						●						
18K 751 E	白 Mn	●				●				●				●
18K 750 A*	白 10% Pd	●				●		●					●	
18K 750 S	白 10% Pd	●	●	●				●					●	
18K 750 CHR*	白 13% Pd				●			●						
18K 750 S2*	白 14% Pd	●		●										
18K 750 M	白 16% Pd	●		●						●				●
18K 750 U	白 12.5% Pd	●	●	●	●	●	●		●	●				●
<b>パラジウム</b>														
PdAg950*	白	●	●	●					●	●	●	●	●	●
<b>プラチナ</b>														
PtIr 800*	白	●						●			●			
PtCo 950*	白					●					●			
PtW 950	白	●						●			●			
PtCu 960	白	●	●	●		●		●	●	●	●		●	●
PtPlus 950	白	●						●			●			●
<b>銀</b>														
Ag 835*	白	●	●	●		●		●						
Ag 925	白					●		●					●	
Ag 935	白	●	●	●		●		●	●				●	●
Ag 970*	白				●									

\*) 特殊合金

上記合金のデータシートなど、詳細に関しましては担当者までお問い合わせ下さい。